

TECHNICAL DATA SHEET

ISONEM LIQUID GLASS

(Liquid Glass - Transparent and Bright Waterproofing)

Product Description

ISONEM LIQUID GLASS is a two-component product which excellent adheres to surface like glass, mosaic, tile, porcelain, ceramic, marble, granite, natural stone, wood, concrete, screed, galvanized sheet, aluminum etc.. The product which has a high resistance to atmospheric conditions can be used for waterproofing and decorative purposes. Produced in transparent the product has high chemical and physical besides excellent water resistance. It is not affected by U.V and outdoor weather conditions. It does not make yellowing, fading or peeling off in time. It is especially applied as a solution to insulation problems arising on the floors such as balconies, terraces, bathrooms easily and without damaging the existing coating.

Usage Areas

- Glass, glass brick, mosaic, mosaic tile,
- Tiles, ceramics, marble, granite, natural stone, porcelain surfaces
- In pressed bricks,
- On wooden surfaces,
- Balcony, terrace, bathroom, kitchen, stone-covered exterior.
- Ceramic, glass mosaic covered ornamental pools.
- It helps to prevent dusting on absorbent surfaces.

Technical Specifications

| | |
|--|--|
| Density A comp. (25°C, g/mL) | : 0,90 ± 0,10 |
| Density B comp. (25°C, g/mL) | : 0,95 ± 0,10 |
| pH (25°C) | : Not applicable (N/A) |
| Viscosity B comp. (25°C, mPa.s) | : 0 - 500 |
| Solid content B comp. (% Weight) | : Not applicable (N/A) |
| Water transmission rate (kg/ m ² . h ^{0.5}) | : < 0,1 CLASS W ₃ |
| Adhesion strength by pull-off test (N/mm ²) | : Rigid system without trafficking ≥ 1.0 N/mm ² |
| Permeability to water vapour (m) | : 5 ≤ S _D ≤ 50 CLASS II |
| Touch-free Drying | : 1 - 2 hours |
| Through-dry time | : 7 days |
| Pot life (23°C) | : 50 – 60 minutes |
| Solvent | : Organic solvent |
| Class of fire reaction | : Bfl S1 |
| Color | : Transparent |

Application Procedure

Surface preparation: The relative humidity of the air should be maximum 80%, the ambient temperature should be 15 - 35 ° C and the surface temperature to be applied should be at least 5 ° C. It should not be applied in rainy weather. For good adhesion, surface cleaning should be done very well. Any kind of oil, dust, dirt, rust and similar substances on the surfaces to be applied between the liquid glass and the floor which may prevent the liquid glass from sticking to the surface should be completely cleaned. In tile, ceramic applications, if existing joint fillings were worn away, they should be renewed. The sanded surface provides better mechanical properties for liquid glass application and helps to better adhesion of the liquid glass to the surface.

Application method: Before application, the two components must be mixed thoroughly and at the given ratios. The two components can react only when the mixture is uniform and complete. The number of floors to be applied for the best performance is indicated in the table below.

Application Conditions / Limitations

| | | |
|---|---|--|
| Application | : | In the same direction as the first layer |
| Surface humidity | : | Dry surface |
| Primer usage | : | X |
| Primer consumption | : | X |
| Product usage | : | For concrete, raw wood, etc. surfaces: 2 layers For marble, granite, tile, ceramic, metal/steel surface; 1 layer |
| Product consumption | : | 150 - 200 g/m ² (two layers), 75 - 100 g/m ² (one layer) |
| Paintable (Coverage) Area | : | 20 - 26 m ² /4 kg set, 10 - 13 m ² /2 kg set |
| Between two coats | : | 4 - 24 hours |
| Recommended application tools | : | Roller (synthetic epoxy), brush, suitable spray |
| Application temperature (°C) | : | 5 - 35 °C |
| Things to consider during and after the application: | | The application surface must be clean and free from all impurities like dirt, oil, and mud. The joint fillings should be renewed if current ones abraded in ceramic, tiles applications. |
| Other ISONEM products recommended: | | - |

IMPORTANT

The surface should be protected from rain, water, mechanical loads and impacts for 24 hours during and after the application. B component should be used immediately after opening. It is not appropriate to re-use an opened packaging that took air.

Packaging & Storage


| | | |
|---------------------------------|---|---|
| Packaging | : | 4 kg set (Component A: 3,3 kg, Component B: 0,7 kg) 2 kg set (Component A: 1,65 kg + Component B: 0,35 kg) |
| Storage temperature (°C) | : | 5 - 35 °C |
| Shelf life | : | 24 months from date of production if stored in original, unopened, undamaged packages. |
| Storage condition | : | Store tightly closed in a dry and cool place away from heat and fire. |

Cleaning of Tools

Clean all tools and application equipment with cellulosic thinner immediately after use.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

| | | |
|--|--|---|
|  2765 | | |
| Isonem Paint and Insulation Technologies Construction Industry Trade Inc. - 35470/IZMIR ITOB OSB 10001 Sok. No:20 Tekeli Menderes / İzmir - TURKEY 19 | | |
| 2765-CPR-0136 TS EN 1504-2: Surface protection systems for concrete - Coating (LIQUID GLASS) DoP No: 17 | | |
| | STANDARD VALUE | CONTROL VALUE |
| Permeability to water vapour | Class I $S_D < 5$ m (permeable to water vapour) Class II $5 \text{ m} \leq S_D \leq 50$ m Class III $S_D > 50$ m (not permeable to water) | Class I - 4 m |
| Capillary absorption and permeability to water | $w < 0,1 \text{ kg/m}^2 \cdot \text{h}^{0,5}$ | $0,05 \text{ kg/m}^2 \cdot \text{h}^{0,5}$ |
| Adhesion strength by pull-off test | Without trafficking $\geq 1,0 \text{ N/mm}^2$ With trafficking $\geq 2,0 \text{ N/mm}^2$ | Rigid system without trafficking $1,0 \text{ N/mm}^2$ |
| Dangerous substances comply with 5.4 | | |
| Class of fire reaction: Bfl S1 | | |

Statement of Responsibility

The technical information and application advice given in this ISONEM Paint & Insulation Technologies publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

